



A-43/2 Nariana Industrial Area
Phase 1, Near PVR Cinema Hall
New Delhi 110028, India
Phone: 011-45612987
Website: www.elan.in



Product Specification Sheet

Pattern: Capote

Date: 4/2/2014

Encore by The Symphony Collection

Description

Weight (<i>linear yard</i>)	20.0 oz
Width	54 "
Thickness	1.00 mm
Gauge	0.04
Emboss	N/A
Surface Composition	100 % Polyurethane (Polycarbonate)
Substrate Composition	100 % Polyester Knit

General Treatments

Hydrolysis Resistance	7 weeks	ISO1419:1995 (<i>Jungle Test</i>)
Colorfastness to Light	200 Hours	(<i>CFFA-2 / AATCC 16-Option 3</i>)
Cold Crack	-20 °F	(<i>CFFA-6a Federal Standard No. 191A-Method 5874</i>)
Mildew Resistant	Pass	(<i>CFFA-120 / ASTM G21-96</i>)
Anti-Bacterial / Anti-Microbial	Pass	(<i>CFFA-300 / AATCC* Test Method 147-1998</i>)
Stain Resistance	with Writer's Block™	
Bleach Resistant	Yes	Diluted 4:1 (20%)

Physical Properties

Abrasion	250,000+ Double Rubs	(<i>CFFA-1A / Method ASTM D 4157-92</i>)
Coating Adhesion	11.4 Warp	10.8 Fill (<i>CFFA 3 / ASTM D751-98</i>)
Tear Strength - Tongue	5.1 Warp	2.9 Fill (<i>CFFA-16b / ASTM D2261-96</i>)
Breaking Strength	144 Warp	113 Fill (<i>CFFA-17 / ASTM D751-10</i>)
Seam Strength - (Tack/Tear)	59.6 Warp	44.4 Fill (<i>CFFA-14 / Method ASTM D751-07</i>)
Blocking Resistance	1 Rating	(<i>CFFA-4 / FTMS 191A-Method 5872</i>)
Crocking	5 Dry	5 Wet (<i>AATCC-Method 8-2001</i>)

Flame Treatments

California Technical Bulletin 117	Pass	NFPA 260	Pass
UFAC Class I	Pass	IMO 2010 FTP Code-MSV 88/26/Add.2 Part 8(3.1)	Pass
BIFMA CS-191-53, Section 3	Pass	ASTM E 84 Un-Adhered : Class 1	Pass
FMVSS 302	Pass		