



A-43/2 Naryana Industrial Area  
Phase 1, Near PVR Cinema Hall  
New Delhi 110028, India  
Phone: 011-45612987  
Website: [www.elan.in](http://www.elan.in)



Product Specification Sheet

**Pattern: Salinger**

Date: 4/2/2014

**Encore by The Symphony Collection**

| <u>Description</u>            |                                    | <u>General Treatments</u>       |  |
|-------------------------------|------------------------------------|---------------------------------|--|
| Weight ( <i>linear yard</i> ) | 20.0 oz                            | Hydrolysis Resistance           | 7 weeks ISO1419:1995 ( <i>Jungle Test</i> )            |
| Width                         | 54 "                               | Colorfastness to Light          | 200 Hours (CFFA-2 / AATCC 16-Option 3)                 |
| Thickness                     | 1.00 mm                            | Cold Crack                      | -20 °F (CFFA-6a Federal Standard No. 191A-Method 5874) |
| Gauge                         | 0.04                               | Mildew Resistant                | Pass (CFFA-120 / ASTM G21-96)                          |
| Emboss                        | N/A                                | Anti-Bacterial / Anti-Microbial | Pass (CFFA-300 / AATCC* Test Method 147-1998)          |
| Surface Composition           | 100 % Polyurethane (Polycarbonate) | Stain Resistance                | with Writer's Block™                                   |
| Substrate Composition         | 100 % Polyester Knit               | Bleach Resistant                | Yes Diluted 4:1 (20%)                                  |

Physical Properties

|                             |                      |                                   |
|-----------------------------|----------------------|-----------------------------------|
| Abrasion                    | 250,000+ Double Rubs | (CFFA-1A / Method ASTM D 4157-92) |
| Coating Adhesion            | 11.4 Warp 10.8 Fill  | (CFFA 3 / ASTM D751-98)           |
| Tear Strength - Tongue      | 5.1 Warp 2.9 Fill    | (CFFA-16b / ASTM D2261-96)        |
| Breaking Strength           | 144 Warp 113 Fill    | (CFFA-17 / ASTM D751-10)          |
| Seam Strength - (Tack/Tear) | 59.6 Warp 44.4 Fill  | (CFFA-14 / Method ASTM D751-07)   |
| Blocking Resistance         | 1 Rating             | (CFFA-4 / FTMS 191A-Method 5872)  |
| Crocking                    | 5 Dry 5 Wet          | (AATCC-Method 8-2001)             |

Flame Treatments

|                                   |      |   |      |
|-----------------------------------|------|---|------|
| California Technical Bulletin 117 | Pass | NFPA 260                                      | Pass |
| UFAC Class I                      | Pass | IMO 2010 FTP Code-MSV 88/26/Add.2 Part 8(3.1) | Pass |
| BIFMA CS-191-53, Section 3        | Pass | ASTM E 84 Un-Adhered : Class 1                | Pass |
| FMVSS 302                         | Pass |   |      |